



RESTORATION WINDOW GLASS

*Mouth-blown, Machine Drawn & Heat Treated*

RESTORATION WINDOW GLASS COMPARISON TABLE

Brand	Crown Glass Heavy Restoration	Old World Colonial™ Light Restoration	Old World Colonial™ Full Restoration	Hollander Circa 1700™	Hollander Circa 1800™	Hollander Circa 1900™	Hollander Circa 1900 Plate™ Glass A-B Quality	Restover™ 3mm / Goethe™ 5mm	Renova™
Description	<i>heavy restoration</i>	<i>light restoration</i>	<i>full restoration</i>	<i>light wave distortion, small pits and other imperfections</i>	<i>medium waves, small pits non directional</i>	<i>light wave restoration non directional</i>	<i>very light waves non directional</i>	<i>light wave restoration vertical lines</i>	<i>very heavy restoration non directional</i>
Stock#	<b>RG MA3CO</b>	<b>RG MA1CO</b>	<b>RG MA2CO</b>	<b>RG 1700H</b>	<b>RG 1800H</b>	<b>RG 1900H</b>	<b>RG 1900PGA RG 1900PGB</b>	<b>RG 0189 RG 0189-5</b>	<b>RG REN-4</b>
Manufacturing Method	<i>mouth blown into disk</i>	<i>mouth blown cylinder</i>	<i>mouth blown cylinder</i>	<i>thermally formed</i>	<i>thermally formed</i>	<i>thermally formed</i>	<i>thermally formed</i>	<i>machine drawn</i>	<i>thermally formed</i>
Origin	<i>Europe</i>	<i>Europe</i>	<i>Europe</i>	<i>USA</i>	<i>USA</i>	<i>USA</i>	<i>USA</i>	<i>Germany</i>	<i>USA</i>
USA Historical Period	<i>1700-1850</i>	<i>1850-1903</i>	<i>1850-1903</i>	<i>1700-1850</i>	<i>†</i>	<i>1900-1928</i>	<i>1900-1928</i>	<i>1914-1950</i>	<i>††</i>
Glass Characteristic	<i>heavy chords, reams</i>	<i>very light chords, occasional bubbles</i>	<i>light chords, occasional bubbles</i>	<i>light diffuse waves</i>	<i>moderate waves occasional pits</i>	<i>moderate diffused waves</i>	<i>very light wave</i>	<i>vertical light waves</i>	<i>heavy diffused waviness</i>
Available Thickness	<i>3mm</i>	<i>3mm</i>	<i>3mm</i>	<i>3mm +- .05mm</i>	<i>3mm, 4mm, 5mm, 6mm, 10mm</i>	<i>3mm, 4mm, 5mm, 6mm, 10mm</i>	<i>3mm, 4mm, 5mm, 6mm, 10mm</i>	<i>3mm, 5mm</i>	<i>3mm, 4mm, 5mm, 10mm</i>
Dimensions	<i>up to 36" x 36" variation</i>	<i>up to 36" x 36" variation</i>	<i>up to 36" x 36" variation</i>	<i>36" x 42" consistent</i>	<i>up to 60" x 84" consistent</i>	<i>up to 60" x 84" consistent</i>	<i>up to 60" x 84" consistent</i>	<i>3mm 40" x 60" 5mm 59" x 83"</i>	<i>up to 60" x 84" consistent</i>
Can it be tempered	<i>no</i>	<i>no</i>	<i>no</i>	<i>no</i>	<i>yes</i>	<i>yes</i>	<i>yes</i>	<i>yes 5mm ONLY</i>	<i>yes</i>
Flatness	<i>minor variations</i>	<i>minor variations</i>	<i>minor variations</i>	<i>good</i>	<i>good</i>	<i>good</i>	<i>good</i>	<i>very good</i>	<i>good</i>

† Although not historically accurate, circa 1800 is a architectural alternative to the Old World Colonial when large sizes do not permit its use.

†† Renova displays a exaggerated waviness for a modern interpretation of the old world look.

F.O.B. our warehouse. Additional freight and boxing charges are applicable.

WWW.RESTORATIONWINDOWGLASS.COM

HOUSTON  
Hollander Glass  
Texas Inc.

Phone: 713-460-0045  
Toll Free: 800-421-0449  
Fax: 713-462-3646

ATLANTA  
Bevel King Doors /  
Hollander Glass

Phone: 678-904-1136  
Toll Free: 877-238-5464  
Fax: 678-904-3360

PHOENIX  
Hollander  
Southwest

Phone: 602-278-9833  
Toll Free: 877-278-9833  
Fax: 602-278-9843

EAST COAST  
Service Center

Hollander Central  
Phone: 732-346-1211  
Fax: 732-346-1711

CANADIAN  
Service Center

Phone: 630-350-2063  
Fax: 630-350-2366